



S.A.P.I.C.I. Spa  
20063 Cernusco sul Naviglio ( MI )  
Via Bergamo, 2  
Tel . (02) 921871; Fax (02) 92141949  
Sito Web: [www.sapici.it](http://www.sapici.it)

## STARTING FORMULATION - N°LAB7761

### 1K PUD HIGH GLOSS WATERBORNE COATING

1	<b>BLUEPUR 2937</b>	86.5
2	Galaster EHL 95 ( not glycol – coalescent )	1.5
3	Byk 024 (defoamer )	1.0
4	Byk 346 (wetting)	1.0
5	Water	10.0
		.....
		<b>100</b>

Add from 1 to 5 under stirring for at least 15 minutes

#### **Characteristics :**

Solid content	30%
Viscosity cup F4	22"
Touch free	35min
Gloss @ 60° 120 micron	90
Hardness	1.5N

*Application by brush or roller 1kg/10 mq*

The above information cannot be guaranteed and we suggest to confirm result in laboratory before plant trials are made. In this respect, the recommendations and formulas given are only suggestion which do not bind either SAPICI or the users.